


Base:  Curing Solution: 

10P8-10NF **EC-283**
4 part 1 part




At 77°F (25°C):

Pot life: **8 Hours**
Induction Time: **None**



Coats needed: **Spray a single uniform wet coat to recommended dry film thickness**
Dry film thickness: **0.8 to 1.2 mils (20 – 30 microns)**



At 77°F ± 2°F 25°C ± 2°C & 55% ± 5% RH

Dust Free: **15 – 30 min**
Tack Free: **30 – 60 min**
Dry Through: **4 Hours**
Clean Up: **MEK or TR-114**



Type equipment	Tip Size	Gun Air Pres.	Pot Air Pres.	Other
Brush				
Roller				

We have taken reasonable care in preparing the Mixing Guide and in collecting and preparing material for inclusion in it but do not represent or warrant that it is free from error or that the information content is complete or accurate. The information is advisory only and the use of the Material is solely at your own risk.